

Takehara Kagaku Kogyo Co., Ltd.

(TAKEHARA CHEMICAL INDUSTRIAL CO., LTD)

Osaka Office

Osaka Daiichi Seimei Building 10F,

1-8-17, Umeda, Kita-ku,

Osaka 530-0001, Japan

TEL: 81-6-4797-1201

FAX: 81-6-4797-1277

HEAD OFFICE

9-7, NAKAZAKI 1-CHOME, AKASHI 673, JAPAN

TOKYO OFFICE

TOEI NISHI-SHINBASHI BUILDING, 13-5, NISHI-

SHINBASHI 1-CHOME, MINATOKU, TOKYO 105, JAPAN

PLANTS

HIROSHIMA, OKAYAMA, FUKUSHIMA

DATA SHEET

NEOLIGHT SP

Surface Coated Precipitated Calcium Carbonate

Made in Malaysia

Applications:

PVC compound, PVC plastisol, Sealant, Adhesive, Paint, Ink

Physical characteristics

	Specification
Coating Agent	Fatty Acid
Particle Size (micron)	0.08 (Typical)
Apparent Specific Gravity (g/cc)	0.23 - 0.37
Whiteness (%)	min 90.0
Moisture (%)	max 1.0
PH	8.5 - 9.5
Oil Absorption (cc/100g)	22 - 26
BET Surface Area (m2/g)	13 - 19