

Unprocessed Products for Industrial Use (Representative Measurement)

Test Item Product Name	Average Particle Size	Residue on 45µm	Whiteness	Moisture Content	Apparent Specific Gravity		DOP Absorption
	µm	% or less	%	% or less	A:g/ml	B:g/ml	ml/100g
NITOREX#23P	1.0	0.00	93	0.4	0.50	1.11	24
NITOREX#80	1.0	0.00	94	0.4	0.24	0.78	-
NITOREX#70	1.2	0.00	94	0.4	0.28	0.89	-
NS#2300	1.0	0.00	94	0.4	0.24	0.80	40
NS#1000	1.2	0.00	94	0.3	0.28	0.90	38
NS#400	1.7	0.00	94	0.3	0.38	1.09	35
NS#100	2.1	0.01	93	0.3	0.46	1.19	32
MM#100	2.2	0.01	95	0.2	0.46	1.19	32
SS#30	7.4	5.0	90	0.2	0.83	1.45	27
NN#500	4.4	0.05	92	0.3	0.70	1.39	28
NN#200	14.8	0.2	90	0.2	0.91	1.49	20
RM#1	5.6	1.0	90	0.3	0.76	1.41	-
RM#2	7.4	20.0	90	0.3	0.83	1.45	-