



Vanderbilt Minerals, LLC

A Wholly Owned Subsidiary of R.T. Vanderbilt Holding Company, Inc.
30 WINFIELD STREET, P.O. BOX 5150, NORWALK, CONNECTICUT 06856-5150 • (203) 295-2140
Fax (203) 855-1220 • Internet Address: www.vanderbiltminerals.com

Specification

DIXIE CLAY®

June 26, 2007

RTV Product Code: **08903**
Composition: Hydrated aluminum silicate, kaolin
Description: White to cream powder

	<u>Specification</u>	<u>Test Method</u>
*Fineness, retained on 325 mesh	0.7% maximum	T-938
*Moisture Content	1.0% maximum	T-936

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Brightness	70
Density at 25°C	2.6 Mg/m ³
Loss on Ignition	14%
Median Particle Size	0.2 µm
Oil Absorption, Rub-Out	42

*Certified Property

Uses - Reinforcing filler and extender for all elastomers and latexes. Used as a filler in non-black stocks and as an extender in black stocks. Reinforces and stiffens uncured and cured stocks. Controls Shrinkage in adhesive compounds. Used in coatings, primers, crack fillers and caulking compounds.

DIXIE CLAY is a registered trademark of R.T. Vanderbilt Holding Company, Inc. and/or its respective wholly owned subsidiaries.

The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Minerals, LLC does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent or to violate any federal, state or local law or regulation.